Computing Grand Challenge Symposium

Toward Petascale Atomistic Simulations with Quantum-Level Accuracy



John A. Moriarty

H Division, Physical Sciences Directorate

February 20, 2008

Co- Investigators: Lin H. Yang, Randy Q. Hood


Collaborations: USC (Vashishta et al.), Harvard (Kaxiras et al.), LANL (Voter et al.)

This work was performed under the auspices of the U. S. Department of Energy by the Lawrence Livermore National Laboratory under contract No. DE-AC52-07NA27344

Motivation: recently funded SciDAC-2 project on stress corrosion cracking (SCC)



- Corrosion is complex technical problem (in e.g., advanced power generation) with annual economic impact equal to 3% of GNP
- USC, Harvard, CSUN, Purdue, LANL, LLNL collaboration
- 5-year goal: develop hierarchical petascale simulation framework to address SCC from first principles
- *LLNL role*: develop new capability to perform ultra-scale atomistic simulations (10⁶–10¹² atoms) with quantum-mechanical accuracy




Materials: *d*-electron transition metals and alloys, e.g., NiAl, at high temperatures

SciDAC focus: advanced simulation capability development

Bridging the gap from quantum mechanics to large scale atomistic simulation






Scientific challenge and strategy



- Scientific challenge: bridge the length and time scale gap from quantum mechanics (~ 100 atoms) to ultra-scale atomistic simulation (billions of atoms) with quantum-level accuracy
- Strategy: Direct coupling of quantum simulations (QMD) and MD simulations with quantum-based multi-ion potentials from model generalized pseudopotential theory (MGPT)
 - ATLAS enabling development of a robust hybrid QMD-MD/MGPT simulation capability for complex d-electron metals and alloys



 Grand challenge goal: simulate 10⁹ atoms at high temperature in prototype systems (e.g., Mo, NiAI) via MD/MGPT with accuracy of direct QMD simulation on 10² atoms

Scope of work and progress to date




- 1) Development and testing of an efficient parallel QMD-MD/MGPT simulation code: *P*³*MD* completed
- 2) Development and application of robust simulation algorithm to optimize MGPT potentials
 - first-generation algorithm established and applied to Mo prototype
 - excellent set of potentials obtained that accurately predict
 atomic structure of liquid Mo
 moving toward optimization
- 3) Establishment of a QMD test data base and corresponding test simulations on derived MGPT potentials: *transferability*
 - extensive two-phase Mo melt simulations in progress
- 4) Billion-atom MD/MGPT demonstration simulations with optimized potentials still to be completed

Hybrid QMD-MD/MGPT simulation code: *P*³*MD*



P³MD = Petascale, Plane-wave, Pseuodopotential Molecular Dynamics



- QMD mode: P³MD implements first-principles pseudopotential method
 - plane wave basis for wavefunction expansion
 - treats 3-9 valence electrons per atom for d-electron transition metals
 - treats 50-250 transition-metal atoms with 1-10 k points
- MD/MGPT mode: P³MD implements model generalized pseudopotential theory


Efficient usage of HPC resources



Parallelization of *P*³*MD* code:

DFT forces: k points, energy bands, plane waves in reciprocal space spread across CPUs in optimal manner, with custom FFT used to move between real and reciprocal space


MD: performed on single CPU, assuming N is small (< 250)



Tests on QMD melt simulations show excellent efficiency

Atlas utilization on grand challenge projects





Average utilization by this project: 300,000 CPU/hours per week

Quantum-based MGPT multi-ion potentials



Total-energy expansion within DFT quantum mechanics

- MGPT potentials derived from systematic simplification of first-principles results
- standard analytic method: canonical d bands (universal form)
- fast matrix method: non-canonical d bands (materials specific form)

$$E_{tot}(R_1, ..., R_N) = NE_{vol}(\Omega) + \frac{1}{2} \sum_{i,j} v_2(ij;\Omega) + \frac{1}{6} \sum_{i,j,k} v_3(ijk;\Omega) + \frac{1}{24} \sum_{i,j,k,l} v_4(ijkl;\Omega)$$
volume radial forces

Three-ion

MGPT: v_3


$$v_4(ijkl;\Omega)$$

$$v_4($$

Importance of electron temperature T_{el}: three limits



- (i) $T_{el} = 0$ and $T = T_{ion}$: low-temperature solid
 - standard assumption in theory, even for high T
 - adequate for most simple sp-bonded materials
- (ii) $T_{el} = T_{ion} = T$: high-temperature solid and liquid
 - important in *d*-electron transition metals due to to high, phase-dependent density of electronic states (DOS)
 - also advantageous: allows one to leverage rich finite-T QMD data
 - in MGPT, include through explicit T-dependent potentials:



$$A_{tot}(R_1, ..., R_N) = NA_{vol}(\Omega, T) + \frac{1}{2} \sum_{i,j} v_2(ij; \Omega, T) + \frac{1}{6} \sum_{i,j,k} v_3(ijk; \Omega, T) + \frac{1}{24} \sum_{i,j,k,l} v_4(ijkl; \Omega, T)$$

volume


radial forces

angular forces

(iii) T_{el} >> T_{ion}: ultra fast laser heating of solid or liquid

QMD-MD/MGPT simulation strategy





Optimization considerations:

- (i) details of MGPT potentials functional form
 - canonical vs non-canonical d bands
 - finite-T systematic improvements
- (ii) choice of constraining data
 - snapshot vs accumulated QMD data
 - additional static solid-phase data

Various options have been tried and a first-generation simulation scheme adopted

Adopted first-generation simulation scheme




MGPT potentials:

- non-canonical d bands
- explicit modeling of T_{el}
 contributions to A_{el}

Constraining data:

- blend of static bcc data at T_{el} + snapshot QMD energies in liquid from 20-30 configurations
- predict accumulated QMD properties as test


Smooth QMD → MD/MGPT transition and rapid convergence:



Simulation conditions: N = 54 atoms, T_{ion} = 10,000 K, Ω = 105.1 au

First-generation Mo potentials accurately predict atomic structure of liquid





Simulation conditions: N = 54 atoms, T_{ion} = 10,000 K, Ω = 105.1 au

Similar results have been obtained over a wide range of volumes at both 5000 and 10,000 K

Two-phase baseline QMD melt simulation in Mo





Parameters of simulation


- N = 256 atoms (minimum size)
- constant T, constant N Ω
- 1-2 ps runs
- 1 k point

Diagnostic strategy

- monitor order parameter (op)
 rather than interface position
- for fixed T, do runs at several volumes of interest








Snapshot of Mo QMD melt: T = 3500 K and P = 35 GPa

Two-phase QMD melt analysis: an example






Same methodology applies to MD/MGPT melt simulations

Mo melt curve: sensitive test of MGPT potentials





For MD/MGPT results:

(c) = *canonical* d bands

(nc) = non-canonical d bands

*early forms of T-dependent MGPT potentials

Additional simulated melt points from QMD and MD/MGPT with current potentials are in progress

Conclusions and expected scientific impact



- A new hybrid QMD-MD/MGPT simulation algorithm has been developed to obtain quantum-level accurate interatomic potentials
 - excellent first-generation MGPT potentials have been developed in a Mo prototype
 - in the coming year, we expect to complete algorithm optimization, potential transferability testing, and initial large scale applications

If we are successful ...

- New predictive science tool for materials extending continuously from nanometers to micrometers
 - essential to SciDAC goal of first-principles SCC multiscale modeling
 - permit fundamental investigations beyond current capabilities
- Will enable accurate advanced programmatic applications
 - non-equilibrium multiphase equations of state with phase kinetics
 - dynamic strength and failure modeling up to micron length scales